

High Performance & Hi-Tg & Lead Free Auto Used NY-A2/NY-A2P

特点 FEATURES:

- Tg170°C 无铅兼容 Tg170°C Lead-free Compatible
- 优秀的剥离强度 Excellent Peel Strength
- 低Z-CTE值 Low Z-axis CTE
- 优秀的耐CAF性能 Excellent Anti-CAF Performance
- UV Blocking和AOI兼容 UV Blocking/AOI Compatible
- 较低的吸水率 Low Water Absorption
- 优秀的尺寸安定性 Excellent Dimension Stability

应用领域 APPLICATIONS:

- 汽车电子 Automotive(Infotainment,Safety system)

NY-A2基板典型性能 Typical Properties for NY-A2 Laminate

属性 Property	项目 Item		测试方法 IPC-TM-650	测试条件 Test Condition	单位 Unit	典型值 Typical Value		
热性能 Thermal	玻璃态转换温度 Tg		2.4.25	DSC	℃	\		
			2.4.24	TMA	℃	170		
			2.4.24.4	DMA	℃	240		
	X/Y轴热膨胀系数CTE,X/Y-axis		2.4.24.5	< Tg,TMA	PPM/℃	13\14		
	Z轴热膨胀系数 Z-axis		2.4.24	< Tg,TMA	PPM/℃	35		
				> Tg,TMA	PPM/℃	170		
			2.4.24	50~260℃	%	1.8		
	热裂解温度 Td		2.4.24.6	TGA(5%W.L)	℃	350		
耐热性 T288		2.4.24.1	Clad	Min	35			
			Etched	Min	50			
电性能 Electrical	介电常数 DK (R/C:55%/70%)		1MHz	2.5.5.9	C-24/23/50	-	4.50\4.05	
			1GHz					4.45\4.00
			10GHz				SPDR method	\
	介质损耗 Df (R/C:55%/70%)		1MHz	2.5.5.9	C-24/23/50	-	0.0156\0.0167	
			1GHz					0.0167\0.0179
			10GHz				SPDR method	\
	体积电阻 Volume Resistivity			2.5.17.1	C-96/35/90	MΩ-cm	2.8×10 ⁸	
	表面电阻 Surface Resistivity					MΩ	2.5×10 ⁷	
物理性能 Physical	吸水率 Water Absorption		2.6.2.1	E-1/105+D-24/23	%	0.08		
	剥离强度 Peel Strength (HTE)	1oz	2.4.8	As Received	N/mm	1.0		
	剥离强度 Peel Strength (RTF)	1oz				\		
	剥离强度 Peel Strength (HVLP)	1oz				\		
	弯曲强度 Flexural Strength		Warp	2.4.4	As Received	N/mm ²	580	
			Fill				460	
	耐燃性 Flame Resistance			UL-94	A&E-4/125	-	V-0	